

10/27/00
JC931 U.S. PTO

10-30-00

A

Please type a plus sign (+) inside this box → ☐

PTO/SB/05 (4/98)
Approved for use through 09/30/2000 OMB 0651-0032
Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number

UTILITY PATENT APPLICATION TRANSMITTAL (Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))	Attorney Docket No.	476-1951
	First Inventor or Application Identifier	Snowdon
	Title	Glass Fiber Fixative and Fixing Process
	Express Mail Label No.	EL 700 383 998 US

APPLICATION ELEMENTS <i>See MPEP chapter 600 concerning utility patent application contents</i>	ADDRESS TO: Assistant Commissioner for Patents Box Patent Application Washington, DC 20231	
1. <input checked="" type="checkbox"/> * Fee Transmittal Form (e.g., PTO/SB/17) (Submit an original and a duplicate for fee processing)	5. <input type="checkbox"/> Microfiche Computer Program (Appendix)	
2. <input checked="" type="checkbox"/> Specification [Total Pages 18] (preferred arrangement set forth below) <ul style="list-style-type: none">- Descriptive title of the Invention- Cross References to Related Applications- Statement Regarding Fed sponsored R & D- Reference to Microfiche Appendix- Background of the Invention- Brief Summary of the Invention- Brief Description of the Drawings (if filed)- Detailed Description- Claim(s)- Abstract of the Disclosure	6. <input type="checkbox"/> Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary) <ul style="list-style-type: none">a. <input type="checkbox"/> Computer Readable Copyb. <input type="checkbox"/> Paper Copy (identical to computer copy)c. <input type="checkbox"/> Statement verifying identity of above copies	
3. <input checked="" type="checkbox"/> Drawing(s) (35 U.S.C. 113) [Total Sheets 4]	ACCOMPANYING APPLICATION PARTS 7. <input type="checkbox"/> Assignment Papers (cover sheet & document(s)) 8. <input type="checkbox"/> 37 C.F.R. § 3.73(b) Statement <input type="checkbox"/> Power of Attorney (when there is an assignee) 9. <input type="checkbox"/> English Translation Document (if applicable) 10. <input type="checkbox"/> Information Disclosure Statement (IDS)/PTO-1449 <input type="checkbox"/> Copies of IDS Citations 11. <input type="checkbox"/> Preliminary Amendment 12. <input checked="" type="checkbox"/> Return Receipt Postcard (MPEP 503) (Should be specifically itemized) 13. <input type="checkbox"/> * Small Entity Statement filed in prior application, Status still proper and desired (PTO/SB/09-12) 14. <input type="checkbox"/> Certified Copy of Priority Document(s) (if foreign priority is claimed) 15. <input type="checkbox"/> Other:	
4. Oath or Declaration [Total Pages] <ul style="list-style-type: none">a. <input type="checkbox"/> Newly executed (original or copy)b. <input type="checkbox"/> Copy from a prior application (37 C.F.R. § 1.63(d)) (for continuation/divisional with Box 16 completed)<ul style="list-style-type: none">i. <input type="checkbox"/> DELETION OF INVENTOR(S) Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).		
* NOTE FOR ITEMS 1 & 13: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).		
16. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment <input type="checkbox"/> Continuation <input type="checkbox"/> Divisional <input type="checkbox"/> Continuation-in-part (CIP) of prior application No. _____ Prior application information. Examiner _____ Group / Art Unit _____ For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.		

17. CORRESPONDENCE ADDRESS					
<input type="checkbox"/> Customer Number or Bar Code Label (Insert Customer No. or Attach bar code label here)	or <input checked="" type="checkbox"/> Correspondence address below				
Name	William M. Lee, Jr.				
	Lee, Mann, Smith, McWilliams, Sweeney & Ohlson				
Address	P.O. Box 2786				
City	Chicago	State	Illinois	Zip Code	60690-2786
Country	USA	Telephone	(312) 368-1300	Fax	(312) 368-6620

Name (Print/Type)	William M. Lee, Jr.	Registration No. (Attorney/Agent)	26,935
Signature	<i>William M. Lee, Jr.</i>	Date	10/27/00

Burden Hour Statement. This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231

FEE TRANSMITTAL for FY 1999

Patent fees are subject to annual revision.
Small Entity payments must be supported by a small entity statement,
otherwise large entity fees must be paid See Forms PTO/SB/09-12

TOTAL AMOUNT OF PAYMENT (\$ 1274

Complete if Known

Application Number
Filing Date
First Named Inventor Snowdon
Examiner Name
Group / Art Unit
Attorney Docket No. 476-1951

METHOD OF PAYMENT (check one)

1. ☒ The Commissioner is hereby authorized to charge indicated fees and credit any over payments to

Deposit Account Number 12-0913
Deposit Account Name Lee, Mann, Smith, McWilliams, Sweeney & Ohlson

☒ Charge Any Additional Fee Required Under 37 CFR 1.16 and 1.17

2. ☒ Payment Enclosed:
☒ Check ☐ Money Order ☐ Other

FEE CALCULATION

1. BASIC FILING FEE

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
101 760	201 380	Utility filing fee	710
106 310	206 155	Design filing fee	
107 480	207 240	Plant filing fee	
108 760	208 380	Reissue filing fee	
114 150	214 75	Provisional filing fee	

SUBTOTAL (1) (\$ 710

2. EXTRA CLAIM FEES

Total Claims	Extra Claims	Fee from below	Fee Paid
38	-20** = 18	18	324
6	-3** = 3	80	240
Multiple Dependent			

**or number previously paid, if greater. For Reissues, see below

Large Entity Small Entity

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description
103 18	203 9	Claims in excess of 20
102 78	202 39	Independent claims in excess of 3
104 260	204 130	Multiple dependent claim, if not paid
109 78	209 39	** Reissue independent claims over original patent
110 18	210 9	** Reissue claims in excess of 20 and over original patent

SUBTOTAL (2) (\$ 564

FEE CALCULATION (continued)

3. ADDITIONAL FEES

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
105 130	205 65	Surcharge - late filing fee or oath	
127 50	227 25	Surcharge - late provisional filing fee or cover sheet	
139 130	139 130	Non-English specification	
147 2,520	147 2,520	For filing a request for reexamination	
112 920*	112 920*	Requesting publication of SIR prior to Examiner action	
113 1,840*	113 1,840*	Requesting publication of SIR after Examiner action	
115 110	215 55	Extension for reply within first month	
116 380	216 190	Extension for reply within second month	
117 870	217 435	Extension for reply within third month	
118 1,360	218 680	Extension for reply within fourth month	
128 1,850	228 925	Extension for reply within fifth month	
119 300	219 150	Notice of Appeal	
120 300	220 150	Filing a brief in support of an appeal	
121 260	221 130	Request for oral hearing	
138 1,510	138 1,510	Petition to institute a public use proceeding	
140 110	240 55	Petition to revive - unavoidable	
141 1,210	241 605	Petition to revive - unintentional	
142 1,210	242 605	Utility issue fee (or reissue)	
143 430	243 215	Design issue fee	
144 580	244 290	Plant issue fee	
122 130	122 130	Petitions to the Commissioner	
123 50	123 50	Petitions related to provisional applications	
126 240	126 240	Submission of Information Disclosure Stmt	
581 40	581 40	Recording each patent assignment per property (times number of properties)	
146 760	246 380	Filing a submission after final rejection (37 CFR 1.129(a))	
149 760	249 380	For each additional invention to be examined (37 CFR 1.129(b))	
Other fee (specify)			
Other fee (specify)			

* Reduced by Basic Filing Fee Paid

SUBTOTAL (3) (\$ 0

SUBMITTED BY

Typed or Printed Name William M. Lee, Jr.

Signature

William M. Lee, Jr.

Date

10/27/00

Complete (if applicable)

Reg. Number 26,935

Deposit Account User ID

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO Assistant Commissioner for Patents, Washington, DC 20231

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICATION FOR LETTERS PATENT

BY

**Kenneth Snowdon
9 Pines Road
Chelmsford
Essex, CM1 2EY
United Kingdom**

**Timothy J. Durrant
4 Tarraway Road
Paignton, Devon
TQ3 2DU
United Kingdom**

**Richard Wilmshurst
9 Wyre Close
Paignton, Devon
TQ4 7RU
United Kingdom**

and

**Christopher G. Tanner
Selangor
Kedington Road
Sturmer, Suffolk
CB9 7XS
United Kingdom**

and

FOR

GLASS FIBER FIXATIVE AND FIXING PROCESS

00698800-103700
002201-0088950

GLASS FIBER FIXATIVE AND FIXING PROCESS

5 Background to the Invention

This invention relates to an fixative for glass fibers and to a glass fiber fixing process. The fixing process and fixative enable glass fibers such as are commonly used in optical communications components to be fixed in position with a hermetic seal.

Optical fibers are relatively thin, fragile strands of glass along which an optical signal propagates. For example, see Fig. 1 of the accompanying drawings for a cross-section of a typical optical fiber. An optical fiber 2 typically comprises an glass fiber core 4 covered by a glass cladding material 6. Typically a primary coating 8a, and secondary outer coating 8b are then used to protect the fiber. The outer coating protects the glass fiber and increases the robustness of the optical fiber.

These outer coatings are typically formed from polymeric materials which have low melting points relative to the glass cladding and core, for example acrylic materials and materials such as thermoplastic polyester, for example Hytrel™. Before the optical fiber can be bonded to another surface, the outer coating must be removed to expose the optical fiber core in the region in which a bond is to be formed. This enables a stronger bond to be formed between the glass fiber material and the other surface element to be bonded.

Forming a strong bond between an optical fiber and an optical component is important as many optical components are subject to vibration. Several problems are associated with the bonding process between a glass material and a non-glass material generally, and the high design specifications for optical components exacerbate these problems.

For example, temperature variations require any bond formed ideally to match the thermal coefficients of expansion of the optical fiber and the bonded part to mitigate thermal stress on the optical fiber. Determining the composition of a glass fixative having a sufficiently low melting point to enable an optical fiber to be bonded to a non-glass material without deforming the optical fiber, having a desired thermal coefficient of expansion, and good adhesive properties to both the silica of the optical fiber and the non-glass material is a difficult and complex task. Alternative processes using solder compounds such as Sn/Pb alloys were employed instead.

Most optical components include parts which have a non-glass composition. For example, metallic materials such as Kovar. One known method of bonding glass to such metallic materials requires the glass fiber to be metalised. The metalisation process required a fiber to be stripped to its core and given a metallic coating consisting of a bonding layer and a soldering layer. This enables bonds between the metalised glass fiber and the Kovar material to be soldered.

Metallisation processes have several disadvantages. The fibers have to have their adhesion verified and any masking material used must be removed. Such metallisation processes are time consuming and the fiber strength can be significantly reduced as a result (typically for example by 30%). Other disadvantages include the extensive handling of fibers required by such processes and the associated high fiber breakage rate, and the capital expenditure on plant required by such processes. A further disadvantage of metalisation processes for fiber fixing is that the soldering process can leave behind potentially corrosive fluxes. The preparation of the fibers for metallisation and soldering is moreover time-consuming. Yet another disadvantage of fiber fixing using metalisation processes is that no reworking is possible during either the metalisation or soldering stages.

In complex optical components, a further problem is the necessity of preventing pre-existing bonds from being degraded when subsequent bonds are formed in the near vicinity.

The bonds must be sufficiently strong and intact form a hermetic seal between the optical fiber and the corresponding portion of the optical component to isolate the interior of the optical component from the external atmosphere. This enables the atmosphere within the optical component to be isolated and for non-air atmospheres or pure air atmospheres to be used. Moreover, the moisture content of the interior can then be controlled. It is thus important for any bond formed to be sufficiently strong to retain the hermiticity of the seal when subject to thermal stress and/or vibration and/or shock.

Summary of the Invention

One object of the present invention seeks to obviate or mitigate the above problems associated with conventional fiber fixing processes by providing a glass fiber fixing process.

Preferably, in the step of forming the bond the preform is heated to a temperature in the range 280°C to 480°C. More preferably, in the step of forming the bond the preform is heated to a temperature in the range 320°C to 370°C.

- 5 In this manner the glass perform is sufficiently melted to flow. In the case where an optical fiber is to be fixed in position within a tube element, the glass is melted sufficiently to flow in a capillary manner between the fiber and the tube.

- 10 A second aspect of the invention seeks to provide a glass fixative for bonding glass elements to non-glass elements, the fixative having a composition including a lead oxide.

- 15 The glass fixative may further include at least one taken from the group including: lead fluoride, and an oxide of: niobium, copper, bismuth, iron, zinc, titanium, aluminum, boron, silicon, and calcium.

- 20 Preferably, the glass fixative has a composition including lead fluoride and an oxide of each of the following: lead, niobium, copper, bismuth, iron, zinc, titanium, aluminum, boron, silicon, and calcium.

- Preferably, the oxide of titanium is titanium dioxide.

- 25 Preferably, the glass fixative composition includes the following: PbO; PbF₂; Nb₂O₅; CuO; Bi₂O₃; Fe₂O₃; ZnO; TiO₂; Al₂O₃; B₂O₃; SiO₂; and CaO.

- 30 More preferably, the glass fixative composition includes the following constituents in the following proportions:

- PbO 60 %wt to 65%wt; PbF₂ 2%wt to 5%wt; Nb₂O₅ 2%wt to 5%wt; CuO 0.5 %wt to 1.5%wt; Bi₂O₃ 6%wt to 7%wt; Fe₂O₃ 2%wt to 3%wt; ZnO 2%wt to 3%wt; TiO₂ 5%wt to 7 %wt; Al₂O₃ 0.1 %wt to 0.3%wt; B₂O₃ 2%wt to 3%wt; SiO₂ 0.1%wt to 0.4%wt; and CaO 1 to 1.5 %wt.

- 35 The glass fixative may have a melting point less than 500°C. Preferably, the glass fixative has a melting point less than 480°C. More preferably, the glass fixative has a melting point between 280°C and 410°C.

Preferably, the glass fixative has a softening point around 320°C to 370°C. The glass fixative preferably has a glass transition temperature between 280°C and 300°C.

Preferably, the glass fixative has a thermal coefficient of expansion of 6 to 8 p.p.m/°C.

- 5 A third aspect of the invention seeks to provide a fixative preform for bonding a glass material element to a non-glass material element, the preform having a composition including lead oxide.

- 10 Preferably, the fixative perform further includes at least one taken from the group including: lead fluoride, and at least one oxide of: niobium, copper, bismuth, iron, zinc, titanium, aluminum, boron, silicon, and calcium.

Preferably, the fixative perform composition includes the following: PbO; PbF₂; Nb₂O₅; CuO; Bi₂O₃; Fe₂O₃; ZnO; TiO₂; Al₂O₃; B₂O₃; SiO₂; and CaO.

- 15 Preferably, the fixative perform composition includes the following constituents in the following proportions:
 PbO 60 %wt to 65%wt; PbF₂ 2%wt to 5%wt; Nb₂O₅ 2%wt to 5%wt; CuO 0.5 %wt to 1.5%wt; Bi₂O₃ 6%wt to 7%wt; Fe₂O₃ 2%wt to 3%wt; ZnO 2%wt to 3%wt; TiO₂ 5%wt
 20 to 7 %wt; Al₂O₃ 0.1 %wt to 0.3%wt; B₂O₃ 2%wt to 3%wt; SiO₂ 0.1%wt to 0.4%wt; CaO 1 to 1.5 %wt.

The fixative preform may further include at least one substance taken from the group including: nickel, cobalt, kovar or magnetite.

- 25 The fixative preform may alternatively include at least one substance taken from the group including: carbon black, graphite, and black metallic oxides.

- 30 A fourth aspect of the invention seeks to provide a glass material bond formed between a glass material element and a non-glass material element. The glass material bond is formed using the glass fixative described above.

Preferably, the glass material element is an optical fiber.

- 35 The non-glass material element may have a metallic characteristic and preferably has a ferromagnetic or ferromagnetic characteristic.

Preferably, the composition of the glass fixative is as described above.

- 40 Preferably, the bond is hermetic.

A fifth aspect of the invention seeks to provide an optical component containing a glass bond, the glass bond having the features described herein.

5 The invention exploits the ferromagnetic characteristic of materials such as Kovar to used induction heating as a means of locally heating a glass preform provided to bond a glass material element in an optical assembly and a non-glass material element. The induction heating advantageously enables the preform to melt to form a hermetic seal between the ferromagnetic material and glass material without unduly heating other portions of the optical assembly.

10 The use of a glass fixative for forming hermetic seals is advantageous as this removes the need to metalise optical fibers. This is advantageous as it obviates the weakening of the optical fibers associated with the metalisation process.

15 Advantageously, the glass fixative enables a relative strong bond to be formed between the optical fiber and another bonding element, which retains the optical fiber in a compressive state. When the glass fixative is used to fix a glass element to a metallic element, in particular to a ferromagnetic element, a localized induction heating process can be used to melt the glass fiber fixative.

20 The composition of the glass fixative is selected so that the thermal expansion coefficient, viscosity, adhesive characteristics and melting point of the glass fixative fall within desired ranges. The ability to select the softening and melting points of the glass fixative is advantageous. A series of bonds can be formed in relatively

25 close proximity to each other, providing the melting point of each successive bond is sufficiently raised above the temperature at which earlier bond(s) soften. The formation of a series of bonds in the vicinity of each other is further enhanced when localized heating is used to melt the glass preforms forming the bond.

30 Advantageously, the glass fixative may melt at a temperature below 400°C. Such low processing temperatures and localized heating help to mitigate damage to the nearby fiber coating, particularly when the coating is formed from a plastic material such as acrylic and Hytrel™.

35 Advantageously, localized heating to be provided such that forming a subsequent bond in the vicinity of an earlier bond results in less thermal stress on the earlier bond. The localized heating method results in the optical bond stressing the optical fiber such that it is bonded in a compressive state. This enhances the ability of the bonded fiber to withstand shock and vibration.

40

Advantageously, the glass preform can be stamped into an annular shape to facilitate positioning of the glass fixative around the optical fiber to be bonded.

Advantageously, the melting point of the glass perform and the viscosity of the molten glass are sufficiently low to enable the melted glass to flow to form an extended bonding area.

Brief Description of the Drawings

For a better understanding of the invention and to show how the same may be carried into effect, there will now be described by way of example only, specific embodiments, methods and processes according to the present invention with reference to the accompanying drawings in which:

Fig. 1 sketches a cross-section of an optical fiber;

Fig. 2 sketches a fiber fixed in position relative to an optical component according to the invention;

Fig. 3 illustrates steps in a glass fixing process; and

Fig. 4 is an enlarged cross-section of the glass fixed fiber joint illustrated in Fig 2 and illustrates how an induction heater can be used as a localized heating source.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

There will now be described by way of example the best mode contemplated by the inventors for carrying out the invention, In the following description numerous specific details are set forth in order to provide a thorough understanding of the present invention. It will be apparent however, to one skilled in the art, that the present invention may be practiced without limitation to these specific details. In other instances, well known methods and structures have not been described in detail so as not to unnecessarily obscure the present invention.

Referring now to Fig. 2 of the accompanying drawings, a glass element, here an optical fiber 10 is bonded by a glass fixative bond 12 to a non-glass material element, here a hypo tube 14. The hypo tube 14 is comprises a non-glass material, for example Kovar, which is a nickel/iron alloy. In other embodiments of the invention other materials may be wish to be bonded to the optical fiber.

The hypo tube 14 is bonded to walls 16 of package 18, either using another glass fixative or a solder bond 19. Within the package 18, the optical fiber 10 extends

10 Generally, the glass bond 12 is formed using a glass fixative having a composition selected to provide several characteristics. The composition is selected to have a suitable softening and melting temperatures, good adhesion to glass and the corresponding non-glass material, a desirably low viscosity, and an appropriate

15 thermal expansion coefficient to provide a strong compressive bond. These characteristics enable a strong, long-lasting bond to be provided between the glass material element and non-glass material element which are to be fixed.

20 The characteristics of the glass fixative for bonding the optical fiber 10 to the Kovar tube 14 were selected to ensure that the bond 12 formed by the glass fixative is hermetic, strong, resilient and matches the thermal coefficients of expansion of both the glass of the optical fiber and the Kovar material. The viscosity is low to enable the bond to form by melted glass flowing in a capillary manner along the tube. The glass fixative also has good adhesion to the glass fiber and the Kovar tube.

25 The composition of a suitable glass fixative is based on lead oxide. A lead oxide based glass has a low melting point glass $< 500^{\circ}\text{C}$. By including an appropriate proportion of bismuth oxide, the softening temperature can be lowered, and a glass with the correct viscosity created which can flow around the Kovar tube and silica

30 glass fiber. Copper oxide and zinc oxides stabilize the melt and prevent devitrification. In addition, zinc oxide increases the environmental stability of the glass seal in ambient atmospheres during use.

35 Whilst the melting temperature of the glass fixative can be selected to lie in the range, 280 °C to 450°C, it is desirable if the upper processing temperature does not exceed 410°C. It is important that the upper processing temperature does not exceed 410°C as this temperature is sufficiently low to ensure that a polymeric fiber coating, for example, acrylic or Hytrel™, is not damaged when the bond is formed. Ideally, therefore, the flow temperature of the glass fixative lies in the range 280°C to 410°C.

volume fraction to the glass preform particles. The particle size distribution is typically centered around 5 microns.

5 In one embodiment of the invention, the glass fixative composition includes filler particles based on magnetite (Fe_3O_4). The magnetite reduces the TEC of the glass fixative and increases the ferrimagnetic coupling to the RF induction heating. This improves the thermal processing of the low melting point glass.

10 In other embodiments, metal fluorides such as PbF_2 are added to the glass fixative to aid wetting of the glass to the silica glass fiber and Kovar by a fluxing action. This lowers the melting temperature of the fixative and removes metal oxides from the Kovar surface.

15 The selected composition of the glass fixative provides a TEC in the range 6.5 to 8.5 p.p.m/ $^{\circ}\text{C}$.

20 The glass fixative used to form a glass bond between a ferromagnetic metallic element and a glass element such as the Kovar tube 14 and the optical fiber 12 of Fig. 2 has the following composition: PbO 60 %wt to 65%wt; PbF_2 2%wt to 5%wt; Nb_2O_5 2%wt to 5%wt; CuO 0.5 %wt to 1.5%wt; Bi_2O_3 6%wt to 7%wt; Fe_2O_3 2%wt to 3%wt; ZnO 2%wt to 3%wt; TiO_2 5%wt to 7 %wt; Al_2O_3 0.1 %wt to 0.3%wt; B_2O_3 2%wt to 3%wt; SiO_2 0.1%wt to 0.4%wt; CaO 1 to 1.5 %wt. Slight modifications to the above composition may be made to bond an optical fiber to other non-glass substances.

25 In a specific embodiment of the invention provided glass fixative having the composition of: PbO 62.5%wt.; PbF_2 3.5%wt; Nb_2O_5 3.5%wt; CuO 1%wt; Bi_2O_3 6.5%wt; Fe_2O_3 2.5%wt; ZnO 2.5%wt; TiO_2 6%wt; Al_2O_3 0.2%wt; Bi_2O_3 2.5% wt; SiO_2 0.25%wt; and CaO 1.25%wt.

30 Referring now to Fig. 3, the process steps in forming glass bond are described. In Fig. 3, a method of forming a bond between a glass element and a non-glass material element such as an optical fiber and an adjacent surface of a kovar hypo tube is described. The method requires a glass surface to be bonded. Therefore,
35 prior to bonding the optical fiber to the kovar hypo tube, removal of the polymeric coating(s) must be completed to expose the glass the fiber core. Typically, the fiber core is exposed for approximately 5mm from the joint region.

40 A glass preform comprising a glass fixative having a composition as described above is then provided in an appropriate position to enable a bond to be formed

between the exposed glass fiber and the Kovar hypo tube. The glass preform comprises the glass fixative described above in a compressed format so that the fixative retains its shape. The preform may be formed under slight pressure. Typically, therefore the preform provides a compressed agglomeration of low melting lead oxide-based glass particles such as previously described.

The preform is positioned on the surface of the glass fiber so that when the preform is heated, then melted, the molten glass flow between the glass fiber and the Kovar in the appropriate place. In practice, the optical fiber is threaded through the Kovar tube and an annular glass preform until the glass preform is positioned adjacent to the Kovar tube. However, other shapes of preform may alternatively be used.

The preform is heated by suitable localized heating means, for example, an induction heater can be used for bonding the optical fiber to a ferromagnetic material such as Kovar. Referring now to Fig. 4, the fiber/hypo tube joint assembly 30 is placed within jaws 32 a, b of an induction heater. The jaws 32 conform sufficiently to the shape of the hypo tube surface to enable inductive currents to be generated within the Kovar tube. Typically, currents of 12 mA are cycled through the Kovar material for 10 to 15 seconds. These currents generate sufficient heat to melt the glass preform so that a strong adhesive bond is formed between the glass fiber and a portion of the interior surface of the Kovar hypo tube. The glass preform flows along the tube as it melts, thus enabling a relatively large bonding area to form. Typically, if the capillary gap between the glass fiber and the inner walls of the hypo tube is l then the capillary action extends the bonding area up to around $3l$ along the direction of the hypo tube axis. This relatively large bonding area provides a high level of support to the fiber.

A fast localized heating mechanism is desirable as it prevents damage to the polymeric fiber coating material during the bonding process. Other fast heat methods can be employed however, providing these can be sufficiently localized, for example, laser heating. Laser heating methods can be used to bond glass to materials which are not suitable for inductive heating methods.

Laser heating effects can be enhanced by incorporating substances in the glass fixative which enhance the absorption of the lasing radiation. For example, carbon black, graphite, or black metallic oxides can increase the glass coupling to CO_2 , Nd/YAG and semiconductor laser heating sources.

When a glass element is to be bonded to a metallic or ferromagnetic material such as Kovar, induction heating is utilized in the best mode contemplated by the

inventor. At least the portion of the tube and fiber to be bonded are positioned in an induction heater. The induction heater provides a suitable induction current which induces current flow in the surface region of the metallic material. The amount of heat generated depends on the type of metallic material and the strength of the inductive currents produced in the surface region of the metallic material.

Heat generated by the induced currents melts the glass preform and the molten glass is able to flow to form a suitable bond. As Fig. 4 shows, the glass melts and is drawn along the tube in a capillary manner so as to form an elongated seal around the optical fiber. As the glass fixative cools it forms a hermetic, compressive seal around the optical fiber which bonds the optical fiber to the adjacent Kovar material of the tube. Typically cooling cycles take 10 seconds.

The inductive heating effect can be increased by doping the glass preform itself with ferromagnetic or ferrimagnetic substances. For example, nickel, cobalt, kovar or magnetite (Fe_3O_4) can be added to the preform to increase the inductive coupling and reduce the heating cycle times below 15 seconds.

In one embodiment of the invention, the induction heater comprises an inducing coil which generates a square pulse of 250-280mA which is generally applied for 10-12 seconds. These conditions are sufficient to heat up, melt the glass preform, wet the Kovar tube and silica fibre and form the hermetic seal.

One specific embodiment of an induction heater comprises an internal coil having a diameter of 3mm and a coil depth of 1.5mm. The internal coil is used to localize heating at the tip of the jaws 32a, b, in the vicinity of the preform. The Kovar tubes are clamped in a non-ferrous jig to ensure that heat is not able to transfer to the plastic fiber coatings. The Kovar tubes are heated in multiples, for example batches of 6 tubes can be heated for 12 seconds. This is an extremely fast process over known processes such as, for example, the time to form a soldered metalised joint which is typically one minute per joint.

The frequency of the induction heater is tuned to 96kHz and heat is localized at the tip of the jaws 32a, 32b in the vicinity of the preform. Temperatures around 350°C are reached using 32kW of power and 12 seconds of applied current.

One embodiment of the invention enables a series of glass bonds to be formed. For example, both the first bond 12 and the second bond 19 sketched in Fig. 2 can be formed from glass fixatives. In Fig. 2, the first bond is a standard hermetic bond between the optical fiber 12 and the Kovar hypo tube 14. The second bond 19 seals

the hypo tube 14 within the package 18. This bond ensures that the optical fiber 10 is aligned with the laser chip 22 within the package 18. To ensure that the formation of the second bond 19 does not damage the first bond 12, the composition of the second glass fixative is modified from the composition of the fixative used to form the first bond 12 to ensure that the melting temperature of the second glass fixative is sufficiently high above the softening temperature of the first glass bond.

Several advantages are provided by using a glass fixative instead of a solder. These include the removal of the necessity to metallize the optical fibers and the ability to form strong bonds in a fast and efficient manner, as well as the ability to rework the bond by softening the fixative.

It is to be understood that modifications and variations can be made to the above description of the invention which have not been explicitly described hereinbefore but which nonetheless are apparent to the person skilled in the art. The scope of the invention is therefore not to be determined by the above description alone but is instead determined by the accompanying claims when construed in conjunction with the accompanying drawings and foregoing description.

- 1 A method of bonding a glass material element and a non-glass material
element using a glass fixative perform, the method comprising the steps of:
- 5 providing a glass preform for bonding the glass material and the non-glass
material;
heating the preform to melt the preform; and
forming a bond with melted glass from the preform, the bond forming
between the glass material element and the non-glass material element.
- 10 2. A method as claimed in Claim 1, wherein in the step of heating the preform, a
source of heat localized to the vicinity of the bond is provided to melt the preform.
3. A method as claimed in Claim 1, wherein in the step of heating the preform,
15 the non-glass material element generates heat which melts the preform.
4. A method as claimed in Claim 1, wherein in the step of heating the glass
preform, an induced current flows in the non-glass material element in the region of
the preform, the induced current generating sufficient heat to melt the preform.
- 20 5. A method as claimed in Claim 1, wherein in the step of heating the preform,
an induction heater is positioned in the vicinity of the bond so as to cause induction
currents to flow in the non-glass material which melt the preform.
- 25 6. A method as claimed in Claim 1, wherein in the step of heating the preform, a
laser heater is provided to heat the glass preform until the glass preform melts
sufficiently to form a bond.
7. A method as claimed in wherein the glass material element is a glass fiber,
30 further including the step of removing non-bonding material from the surface of an
optical fiber to expose a portion of glass fiber to be bonded.
8. A method as claimed in Claim 1, wherein in the step of forming the bond the
preform is heated to a temperature in the range 280°C to 480°C.
- 35 9. A method as claimed in Claim 1, wherein in the step of forming the bond the
preform is heated to a temperature in the range 320°C to 370°C.
10. A glass fixative for bonding glass elements to non-glass elements, the
40 fixative having a composition including a lead oxide.

11. A glass fixative as claimed in Claim 10, further including at least one taken from the group including: lead fluoride, and an oxide of: niobium, copper, bismuth, iron, zinc, titanium, aluminum, boron, silicon, and calcium.
- 5
12. A glass fixative as claimed in Claim 10, wherein the glass fixative has a composition including lead fluoride and an oxide of each of the following: lead, niobium, copper, bismuth, iron, zinc, titanium, aluminum, boron, silicon, and calcium.
- 10
13. A glass fixative as claimed in Claim 10, wherein the glass fixative composition includes the following: PbO ; PbF_2 ; Nb_2O_5 ; CuO ; Bi_2O_3 ; Fe_2O_3 ; ZnO ; TiO_2 ; Al_2O_3 ; B_2O_3 ; SiO_2 ; and CaO .
- 15
14. A glass fixative as claimed in claim 10, wherein the glass fixative composition includes the following constituents in the following proportions:
 PbO 60 %wt to 65%wt; PbF_2 2%wt to 5%wt; Nb_2O_5 2%wt to 5%wt; CuO 0.5 %wt to 1.5%wt; Bi_2O_3 6%wt to 7%wt; Fe_2O_3 2%wt to 3%wt; ZnO 2%wt to 3%wt; TiO_2 5%wt to 7 %wt; Al_2O_3 0.1 %wt to 0.3%wt; B_2O_3 2%wt to 3%wt; SiO_2 0.1%wt to 0.4%wt; and CaO 1 to 1.5 %wt.
- 20
15. A glass fixative as claimed in Claim 10, wherein the glass fixative has a melting point less than 500°C.
- 25
16. A glass fixative as claimed in Claim 10, wherein the glass fixative has a melting point less than 480 °C.
- 30
17. A glass fixative as claimed in Claim 10, wherein the glass fixative has a melting point between 280°C and 410°C.
- 35
18. A glass fixative as claimed in Claim 10, wherein the fixative has a softening point around 320°C to 370°C.
19. A glass fixative as claimed in Claim 10, wherein the fixative has a transition temperature between 280°C and 300°C.
20. A glass fixative as claimed in Claim 10, wherein the fixative has a thermal coefficient of expansion of 6.5 to 8.5 p.p.m./°C.

21. A fixative preform for bonding a glass material element to a non-glass material element, the preform having a composition including lead oxide.
- 5 22. A fixative preform as claimed in Claim 21, wherein the fixative preform further includes at least one taken from the group including: lead fluoride, and at least one oxide of: niobium, copper, bismuth, iron, zinc, titanium, aluminum, boron, silicon, and calcium.
- 10 23. A fixative preform as claimed in Claim 21, wherein the fixative preform composition includes the following: PbO ; PbF_2 ; Nb_2O_5 ; CuO ; Bi_2O_3 ; Fe_2O_3 ; ZnO ; TiO_2 ; Al_2O_3 ; B_2O_3 ; SiO_2 ; and CaO .
- 15 24. A fixative preform as claimed in Claim 21, wherein the fixative preform composition includes the following constituents in the following proportions:
 PbO 60 %wt to 65%wt; PbF_2 2%wt to 5%wt; Nb_2O_5 2%wt to 5%wt; CuO 0.5 %wt to 1.5%wt; Bi_2O_3 6%wt to 7%wt; Fe_2O_3 2%wt to 3%wt; ZnO 2%wt to 3%wt; TiO_2 5%wt to 7 %wt; Al_2O_3 0.1 %wt to 0.3%wt; B_2O_3 2%wt to 3%wt; SiO_2 0.1%wt to 0.4%wt; CaO 1 to 1.5 %wt.
- 20 25. A fixative preform as claimed in Claim 21, wherein the preform bonds an optical fiber to a metallic element.
- 25 26. A fixative preform as claimed in Claim 21, further including at least one substance taken from the group including: nickel, cobalt, kovar or magnetite.
27. A fixative preform as claimed in Claim 21, further including at least one substance taken from the group including: carbon black, graphite, and black metallic oxides.
- 30 28. A glass material bond formed between a glass material element and a non-glass material element with a glass fixative.
29. A bond as claimed in Claim 28, wherein the glass material element is an optical fiber.
- 35 30. A bond as claimed in Claim 28, wherein the non-glass material element has a metallic characteristic.
- 40 31. A bond as claimed in Claim 28, wherein the non-glass material element has a ferromagnetic characteristic.

32. A bond as claimed in Claim 28, wherein the non-glass material element has a ferrimagnetic characteristic.
- 5 33. A bond as claimed in Claim 28, wherein the glass fixative includes a lead oxide.
34. A bond as claimed in Claim 28, wherein the glass fixative further includes at least one taken from the group including: lead fluoride, and at least one oxide of:
10 niobium, copper, bismuth, iron, zinc, titanium, aluminum, boron, silicon, and calcium.
35. A bond as claimed in Claim 28, wherein the glass fixative composition includes the following: PbO ; PbF_2 ; Nb_2O_5 ; CuO ; Bi_2O_3 ; Fe_2O_3 ; ZnO ; TiO_2 ; Al_2O_3 ; B_2O_3 ; SiO_2 ; and CaO .
15
36. A bond as claimed in Claim 28, wherein the glass fixative composition includes the following constituents in the following proportions:
 PbO 60 %wt to 65%wt; PbF_2 2%wt to 5%wt; Nb_2O_5 2%wt to 5%wt; CuO 0.5 %wt to 1.5%wt; Bi_2O_3 6%wt to 7%wt; Fe_2O_3 2%wt to 3%wt; ZnO 2%wt to 3%wt; TiO_2 5%wt
20 to 7 %wt; Al_2O_3 0.1 %wt to 0.3%wt; B_2O_3 2%wt to 3%wt; SiO_2 0.1%wt to 0.4%wt; CaO 1 to 1.5 %wt.
37. A bond as claimed in Claim 26, wherein the bond is hermetic.
- 25 38. An optical component containing at least one glass bond.

Glass Fiber Fixative and Fixing Process

Abstract

- 5 A glass fixative composition for bonding glass materials to non-glass materials is provided. The fixative composition is selected for its thermal expansion coefficient, its viscosity, its adhesion to glass, melting point, and bond strength. The glass fixative is in particular useful for bonding optical fibers to metallic materials such as Kovar. The low melting point of the glass fixative enables localized heating methods to be used, in particular, as Kovar is a ferromagnetic material, induction heating can
- 10 be used to form a bond. The bond formed provides a compressive joint which enables the fiber to be hermetically fixed in position.

00698800 102700




FIG 1




FIG 2




FIG 3




FIG 4